



Current Status of Laser Welding for Bipolar Plates in Proton Exchange Membrane Fuel Cells

**Jiale Peng ^{a*}, Pengyan Guo ^a, Wanxiang Yin ^a,
Jiabao Wei ^a, Ning kang Bian ^a and Hao Xing ^a**

^a *North China University of Water Resources and Electric Power, Zhengzhou 450002, Henan, China.*

Authors' contributions

This work was carried out in collaboration among all authors. All authors participate in literature review and summarize the literature. All authors read and approved the final manuscript.

Article Information

DOI: <https://doi.org/10.9734/jerr/2024/v26i101302>

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/123803>

Review Article

Received: 17/07/2024

Accepted: 19/09/2024

Published: 09/10/2024

ABSTRACT

Hydrogen fuel cells have become a hot research topic in recent years. Bipolar plates are the core components of fuel cells and the bipolar plate accounts for 70% of the total weight of the fuel cell, and laser welding is considered one of the most suitable technologies for fuel cell bipolar plate welding. This article summarizes the current research status in the field of fuel cell bipolar plate laser welding, which can clearly represent the latest achievements in the field of fuel cell bipolar plate welding. This article's research on fuel cell bipolar plates can serve as a fundamental understanding and reference, providing background guidance for future research. However, current research on bipolar plates is still too idealistic and has not been combined with engineering practice. Future researchers can study the welding of fuel cell bipolar plates from the perspective of engineering practice.

*Corresponding author: Email: 2013216701@qq.com, 19513327195@163.com;

Cite as: Peng, Jiale, Pengyan Guo, Wanxiang Yin, Jiabao Wei, Ning kang Bian, and Hao Xing. 2024. "Current Status of Laser Welding for Bipolar Plates in Proton Exchange Membrane Fuel Cells". *Journal of Engineering Research and Reports* 26 (10):239-49. <https://doi.org/10.9734/jerr/2024/v26i101302>.

Keywords: *Hydrogen energy; hydrogen fuel cell; energy transition; carbon neutrality; new energy technology; fuel cell vehicles; domestication; energy policy.*

1. INTRODUCTION

In the research of hydrogen fuel cell vehicles, the study of proton exchange membrane fuel cell bipolar plates plays a crucial role. A hydrogen fuel cell consists of a membrane electrode, a bipolar plate, and a diffusion layer. The bipolar plate plays an important role in distributing reaction gases and supporting the membrane electrode. At the same time, the bipolar plate accounts for 60% of the mass and nearly 40% of the cost of the fuel cell, making it an indispensable and important component of the hydrogen fuel electric vehicle. In terms of material selection for bipolar plates, stainless steel has good conductivity, excellent plasticity, and low cost, making it extremely suitable for stamping and welding processing methods. It is very suitable as a raw material for processing bipolar plates. The general method for welding and processing stainless steel bipolar plates is laser welding. Laser welding, as a popular welding method in recent years, has the advantages of high precision, fast speed, and small heat affected zone, which is very suitable for the welding requirements of metal bipolar plates. Meanwhile, laser welding can be applied in large-scale production, making it favored by industry companies.

2. EMPIRICAL REVIEW

Ahmad Aminzadeh et al. [1] experimentally studied the effects of important process factors such as welding speed, billet clamping force (BHF), base material properties, drying/lubrication conditions, and laser spot size on the motion of weld lines and deep drawing. The conclusion was drawn that using LBW with optimal parameters to produce heterogeneous TWB can control the failure of weaker base materials.

Malaya Prasad Behera et al. [2] proposed a typical point by point consolidation mechanism for additive manufacturing as a possible means of enhancing control over the composition of metal matrix composites. The selective laser melting composite material 3N4 with stainless steel 316L as the base material and Si as the filling stage was evaluated in the current study, and it was concluded that under appropriate process conditions, the tensile strength of the composite material was better than that of pure 316L when laser melted.

Yu Qiu et al. [3] reevaluated the fatigue reliability of thin plate welded joints using the JC method and concluded that the reliability index of thin plate welded joints is closely related to the plate thickness, and the tolerances recommended by traditional specifications should be corrected for the plate thickness.

Yongjian He et al. [4] studied the welding heat distribution state and its influence on welding deformation by adjusting the laser welding sequence. They used numerical simulation and experimental research to investigate the welding deformation of 1mm 6061 aluminum alloy thin plate by laser welding. The results show that the transverse shrinkage of segmented skip welding with a single weld is smaller, the longitudinal shrinkage is better controlled, and the out of plane deformation is lower than that of continuous welding with a single weld.

Sukanta Das, R et al. [5] studied and designed a friction stir spot welding method using consumable sheet metal (FSSW-C), which can be used to connect different sheets.

Sami Lininalampi et al. [6] studied the fatigue strength of 3mm thick laser hybrid welded butt joints using measured microscale weld geometry and notch stress methods. The notch stress is defined using Neuber's stress averaging method, which allows for the determination of effective fatigue stress without the need for fictitious geometric modifications.

Vanessa Bawden de Paula Macanhan et al. [7] studied the natural frequency variation of welded thin plates. Experimental analysis was conducted on 8 AISI316LSS plates with a thickness of 6.30mm, including beads on board (BOP) and butt welding. The results indicate that the variation of the first torsional mode is significant, while the variation of the longitudinal bending mode is around zero.

Pengfei Zhao et al. [8] used an AC-300 W pulse laser welding machine to weld 1 mm magnesium alloy at preheating temperatures of 25 °C, 100 °C, 150 °C, 200 °C, 250 °C, 300 °C, and 350 °C, respectively. They studied the effects of different preheating temperatures on solidification cracks, porosity, and undercutting. The results showed that preheating increased the peak temperature of the molten pool, reduced the cooling rate of

the molten pool, and thus reduced the sensitivity of welding defects.

Tobias Valentino et al. [9] investigated a new method of reducing bending angle dispersion by modifying the residual stress state of thin plates before the forming process. It has been proven that the thermal mechanism plays a dominant role in the deflection of the sheet metal, and laser pretreatment increases the robustness of subsequent bending operations.

Jayanta Ghosh Roy et al. [10] applied cold metal transfer technology to welding AISI 304 stainless steel and selected various welding process parameters, such as welding current, welding speed, and contact working distance, to study the welding strength characteristics. Conclusion: There is no fracture at the weld seam; The residual tensile stress levels of all samples are in a controlled state; Welding speed is the most important welding process parameter, followed by the influence of welding current and contact working distance on the tensile strength of welded joints.

Jae et al. [11] conducted thermal elastoplastic simulation on the laser welding process of I-core sandwich panels. In the welding simulation, an improved conical heat source model was first proposed, and the reliability of the heat source model was verified through welding experiments. Then, the improved heat source model was used to study the effects of welding power, welding speed, and other post weld deformations. The results showed that welding power was positively correlated with post weld deformation, while welding speed was negatively correlated with post weld deformation.

Harald Schlag from the United States used vacuum clamping to clamp bipolar plates and conducted laser welding tests on metal bipolar plates. Through experiments, it was found that using vacuum clamping bipolar plates for laser welding results in higher weld strength and stronger corrosion resistance of bipolar plates. However, due to the need for vacuum pumping in this clamping method, the welding cost of the metal bipolar plate increases.

Mato Peri ć et al. [12] proposed an effective thermoplastic method for predicting welding induced deformation in large panel structures. Two numerical examples were analyzed to evaluate the accuracy and effectiveness of the method. The results indicate that shell/3D

modeling technology significantly reduces the computation time required for simulating welding processes, enabling effective thermal elastoplastic analysis of large structures.

Ninshu Ma et al. [13] conducted a quantitative study on the influence of fixture constraints on welding deformation. The welding deformation of square bead welding plates under unconstrained and fixture constrained conditions was studied through experiments. The results show that fixture constraints greatly reduce welding angle deformation, and simulation and experiment have good consistency.

3. THEORETICAL REVIEW

Nikhil Kumar [14] conducted welding tests on 304 stainless steel and 316L stainless steel separately, and compared the mechanical strength of their welds. The results showed that compared with 316, 304 requires higher linear energy to achieve maximum ultimate tensile strength and minimum weld width. The pulse width is the most important factor affecting the ultimate tensile strength of 304 and 316, followed by laser power and scanning speed. Laser power is the most important factor affecting the width of 304 weld seam, followed by scanning speed and pulse width. The laser power is the only important parameter that affects the width of the 316 weld seam.

Morgan Dal et al. [15] briefly explained the methods of numerical simulation for welding, dividing the simulation into thermodynamic simulation and multiphysics simulation, and proposed the problems and improvement methods of these two simulations.

Lijun Han et al. [16] determined laser beam indicators such as focusing index by studying the internal relationship between laser parameters and welding laser characteristics. Simplify it to a small number of laser parameters to facilitate the study of the influence of welding parameters on the forming coefficient. The results indicate that material, assembly clearance, laser power, and welding speed have a significant impact on weld penetration. When the laser power density reaches 106 J/cm², the characteristic of deep penetration welding occurs. Under the condition of constant gap, the depth of the weld increases with the increase of t/b. The weld seam increases with the increase of laser power and tends to stabilize when the welding speed is 12 mm/s.

Wojciech Suder [17] studied the formation law of laser welding weld pool through fluid dynamics simulation and high-precision camera observation. It was found that the main cause of Marangoni convection in conductive laser welding or laser wire melting process can be controlled separately through beam forming; And a new concept of dynamic beam forming was proposed, and its ability to freely adjust the melt flow was demonstrated.

Zun Yue Huang et al. [18] measured the welding bending distortion of 1mm thick AA5052 aluminum using digital image correlation technology after laser welding. Two mathematical response models for predicting laser welding bending deformation were established based on the rotatable design method of central composite materials. The conclusion was obtained that the minimum welding bending deformation was achieved within the working range at a laser power of 900 W, a welding speed of 9 mm/s, a defocusing distance of 2 mm, and a gas flow rate of 25 L/min.

Shichun Li et al. [19] used laser hot wire welding technology to weld 7075 high-strength aluminum alloy. Analyzed the influence of parameters on weld formation during laser hot wire welding process, and analyzed the microstructure characteristics and mechanical properties of the weld. The results indicate that the parameters that affect the formation of welds from high to low include laser power, current, gap width, welding speed, and wire supply rate. As the temperature of the welding wire increases, the quality of the weld seam formation decreases successively.

Salman Nisar et al. [20] conducted transient thermal analysis on AA5083 aluminum alloy and studied the parameterized effects of laser power and welding speed on the peak temperature, aspect ratio of weld width and depth, and width of heat affected zone of samples with different thicknesses. The results indicate that laser power has a significant impact on weld width, and welding speed has a significant impact on peak temperature.

Danny et al. [21] used a YAG laser beam to weld 60 μ m AISI 304 (a type of austenitic stainless steel) stainless steel sheet. The results show that compared with resistance welding, laser welding requires nearly three times less heat input, produces a 50% narrower weld seam, reduces porosity by 15%, and increases strength by 25%.

It overcomes obstacles such as excessive deformation, formation of discontinuities (pores, voids, and thermal cracks), uncontrolled melting, and poor aesthetics.

Brady et al. [22] also used laser welding in the design of advanced metal bipolar plate connections. In this design, 0.1 mm thin foils of Fe-20Cr-4V and Fe-23Cr-4V are processed through stamping technology and then laser welded under argon protection to produce metal bipolar plate components for the anode and cathode, including cooling channels. Then, the laser welded plate is subjected to surface treatment through pre oxidation and nitriding.

The process parameters of laser welding have a significant impact on the welding quality. In order to improve the quality of laser welding, Pakmanesh et al. [23] studied the effect of Nd: YAG pulse laser welding process parameters on the corrosion resistance of metal bipolar plates after welding. The results indicate that reducing the peak power, duration, and frequency of the pulse will decrease the corrosion current density of the sample, with the pulse duration having the greatest impact.

Nawi et al. [24] used an ultra short pulse Nd: YAG laser with a wavelength of 1064 nm to perform spot welding on 304 stainless steel. We studied the effects of laser welding parameters, including peak power of the laser beam, pulse duration, incident angle, focal position, and number of shots, on the size of the weld seam (penetration depth and weld width). The results show that the penetration depth and width increase with the increase of welding power, pulse duration, and number of shots. However, as the laser defocusing amount and incident angle increase, the penetration depth and width decrease.

Liao et al. [25] used pulsed Nd: YAG laser to weld stainless steel samples. The laser energy range is 0.6-1.2J, and the incident angle (the angle at which the laser beam is incident on the surface of the plate) is 30-75 °. Research has found that with the increase of laser energy, the penetration depth, weld bead length, and weld bead width of the molten pool all increase. As the laser incidence angle increases, the melting depth and width also increase.

Venturella et al. [26] used a YAG laser to weld 100 μ m AISI 316L stainless steel plates. The laser pulse energy ranges from 1.0 J to 2.25 J,

with increments of 0.25 J, and the pulse duration is 4 ms. The results indicate that pulse energy control is of great significance for the welding quality of thin plates, as it can generate good mechanical properties and reduce the discontinuity of welded joints. As the pulse energy increases, the maximum tensile strength of the welded joint first increases and then decreases.

Liu et al. [27] proposed a new method of synchronous heat dissipation and ultrasonic hybrid laser welding (SHS+UHLW). We established simulation models for synchronous heat sink assisted laser welding (SHSLW), ultrasonic assisted laser welding (UALW), and SHS+UHLW for comparison, and studied the distribution of stress and deformation under different welding processes. The results showed that compared with conventional laser welding, SHSLW, UALW, and SHS+UHLW all reduced the residual stress and post weld deformation of the weld seam. Among them, SHS+UHLW has a more significant reduction effect, with stress and deformation reduced by 8% and 40% respectively. In the SHS+UHLW process, the ultrasonic cavitation effect and cooling are used to refine the grain size of the weld seam to the maximum extent, thereby improving the mechanical properties of the weld seam. Compared with LW, the hardness and tensile mechanical properties of SHS+UHLW joint have increased by 11.8% and 13.62%, respectively. Therefore, this method not only reduces the deformation of thin plates, but also improves the mechanical properties of welds, achieving coordinated control of welding deformation and weld performance.

Deng et al. [28] optimized the welding deformation of stainless steel plates by changing the welding process parameters. The results indicate that different heat inputs have a significant impact on both lateral and longitudinal deformation, and bending deformation increases with increasing heat input.

Adak [29] placed a cooling system (water circulation) under the welding plate to regulate the temperature of the welded thin plate. Experimental results showed that placing a cooling system under the lower plate can significantly reduce welding deformation by about 41%. However, the cooling system accelerates the cooling rate of the molten pool, greatly reducing the forming quality of the weld and thus lowering the performance of the weld.

Zhan [30] placed the specimen at a certain angle in the opposite direction of deformation before welding, which is called the reverse deformation method. The key to implementing this method is to design specific fixtures. The influence of welding sequence on deformation was analyzed using ANSYS, and a new welding sequence was proposed to reduce welding deformation.

Guirao [31] studied "the effect of heat input on the deformation and stress of a thin plate with a thickness of 0.5 mm during micro arc welding. In the experiment, copper fixtures were used to constrain the sample, resulting in faster cooling in the thickness direction, smaller temperature gradients, and reduced angular deformation. The laser magnetic welding of L steel plate shows that the magnetic field is beneficial for reducing the transverse direction".

Rong et al. [32] studied "hybrid laser magnetic welding of 316L stainless steel. A new simplified heat source model was developed to simulate temperature distribution, taking into account the influence of magnetic field on the geometry of magnetic beads. Combining steady-state magnetic field with laser welding reduced angular deformation by 26.56%, longitudinal residual stress decreased, and transverse tensile stress decreased from 199.1 MPa to 167.3 MPa. Laser magnetic welding helps to improve the quality of the weld bead, reduce angular deformation, residual stress, and plastic strain".

Zhang [33] proposed "a multi beam preheating method to reduce distortion. Yi et al. successfully utilized transient thermal tension technology to reduce buckling deformation during thin plate welding. There are also some control techniques based on mechanical methods, such as the prestressing method".

Casalino et al. [34] used laser offset welding to connect AZ31B magnesium alloy and 316 stainless steel into a butt joint structure. The results indicate that the use of adhesive welding method can effectively avoid many drawbacks of laser welding between magnesium and stainless steel. It can produce good metal welds, with good tensile strength and effective connections.

Tao et al. [35] enhanced the performance of laser welded joints between AZ31B magnesium alloy and DP590 duplex steel using pre fabricated groove structures with external and added Sn powder. The results indicate that plasma has a shielding effect on laser energy, thereby improving the absorption rate of laser

energy. This promotes the "bidirectional" metallurgical bonding of the magnesium/steel interface, thereby improving the mechanical properties of the magnesium/steel joint.

Suman et al. [36] performed nanosecond laser welding on Al Cu and Cu Al joints. The results showed that by changing the laser power, Al Cu welds exhibited better microstructure, with fewer voids and cracks compared to Cu Al welds.

Shu et al. [37] conducted welding experiments on 316L stainless steel and 6063 alloy thin plates with different line distances. The results indicate that when the line spacing is 0.02 mm, an oxide free joint is obtained, and thermal conductivity decreases with increasing line spacing.

Abderrazak et al. [38] established a three-dimensional transient heat source model using the Goldak volume method and studied the thermal fluid flow in laser welding of magnesium alloys. This study reveals the influence of surface tension temperature coefficient and Marangoni convection on the formation of molten pools.

Artinov et al. [39] established an equivalent volume heat source model for predicting the temperature and weld bead profile of alloy steel laser welding, and the numerical results showed good correlation with experimental results. In one of the studies, the authors demonstrated that by changing or modifying the heat source parameters, the heat source model used for numerical simulation of laser welding can be adjusted to produce better results similar to experiments.

Wu et al. [40] established a three-dimensional conical heat source model and conducted thermal and static analysis on 304 stainless steel using ANSYS. The welding process, molten pool morphology, and post weld deformation were observed and verified through experiments. The final experiment showed that the simulation results matched well with the experimental results.

Aghaee Attar et al. [41] studied six different thermal distribution models for thermal and mechanical analysis of 304 stainless steel and copper dissimilar laser welding. Rahman Chukkan et al. [42] compared the prediction of temperature, residual stress, and deformation in laser welding of 316L stainless steel using different heat source models, including 3D cone, 3D cone and double ellipsoid composite heat sources, and combined 3D cone and cylindrical

composite heat sources. The numerical results indicate that the 3D conical and cylindrical composite heat source can accurately predict the residual stress and deformation of thin plates after welding.

Ahmad et al. [43] successfully "welded the super alloy Inconel 625 and duplex stainless steel 2205 (DSS 2205) using a fiber laser with different heat inputs. As the energy input decreases, the width of the weld seam narrows and the mechanical properties of the joint improve. Characterization of welded joints using scanning electron microscopy (SEM), energy dispersive spectroscopy (EDS), X-ray diffraction (XRD), and microhardness testing. No solidification cracks or porosity were observed in the microstructure of the weld metal (WM). Honeycomb shaped dendritic and columnar dendritic grains are the main grain types observed in welded metals. At a heat input of 43 J/mm, there was more molybdenum and niobium segregation in the interdendritic arms of the weld metal compared to the sample welded at a heat input of 21.5 J/mm. Research on tensile strength shows that when the provided heat is low (i.e. 21.5 J/mm), the maximum strength is 890 MPa. This strength value is greater than the strength value of the base material (DSS 2205). The results obtained from the comprehensive correlation between structure and characteristics recommend the effectiveness of laser beam welding for the joining of the dissimilar alloys".

MIS Ismail et al. [44] established "a three-dimensional finite element model to simulate the temperature, stress, and deformation fields in continuous wave (CW) laser micro welding of stainless steel thin plates. Welding deformation was evaluated experimentally using a single-mode fiber laser with a high-speed scanning system. The application of the developed thermal model shows that laser parameters (such as laser power, scanning speed, and spot diameter) have a significant impact on the temperature field and weld pool. Numerical simulations were conducted using a non coupled thermodynamic model in the case of welding deformation. During heating and cooling, plastic deformation can generate welding stress and deformation. It can be confirmed that residual stress is higher than the yield strength and has the greatest impact on welding deformation. The numerical simulation results demonstrate that the developed finite element model can effectively predict the thermal cycling, thermal stress, and welding deformation of thin materials".

P Pankaj et al. [45] conducted “experiments and numerical analysis on CO₂ laser welding of AISI 304 stainless steel plate with a thickness of 1 mm. Predicting transient thermal history is crucial when designing welded joints. A 3D finite element model was developed using ANSYS to determine the influence of welding process parameters (i.e. laser power and welding speed) on the thermal history of laser welded joints. The influence of weld geometry obtained from experiments was considered in this 3D finite element model to simulate a moving volumetric heat source. The element birth and death technique is used in finite element thermal analysis to simulate the progress of laser welding zones. It is observed that the cooling rate is greatly affected by changes in laser power and welding speed. It was also observed that increasing laser power and decreasing welding speed would lead to an increase in the size of the fusion zone and heat affected zone. The transient thermal analysis results obtained from the finite element model and experimental results have been well validated, with a maximum percentage error of 6.47% for peak temperature”.

Kim et al. [46] studied “a hybrid welding process that combines TIG arc welding with YAG laser. Especially, the welding conditions suitable for thin steel plate welding were studied, and welding results with beautiful surface and back weld beads but no welding defects were obtained. During the research process, it was confirmed that the emission position of the laser beam is crucial for achieving good welding in hybrid welding. Therefore, a new intelligent system using visual sensors to monitor the welding area has been constructed. In addition, a control system was constructed to emit the laser beam to a selected position in the molten pool, which is formed by TIG arc. The results of welding experiments using these systems indicate that the hybrid welding process and control system are effective for stable welding of thin stainless steel plates”.

Farid [47] studied “the precise seam welding ability of a photolytic iodine laser (PIL) on a 0.1mm thick AISI 316 stainless steel sheet in a lap structure. The welding performance data of PIL laser was compared with Nd: YAG and CO₂ lasers. The advantages of PIL welds include narrow seams, extremely fine solidification unit structure, complete austenitic structure, and smaller heat affected zone (HAZ). In contrast, the welds produced by Nd: YAG and CO₂ lasers

exhibit wider seams, coarser solidification structures, dual phase microstructures of austenite and ferrite, and larger heat affected zones due to slow cooling and transverse thermal diffusion of the melt”.

M. Zain Ul Abdein et al. [48] studied the thermal mechanical response of thin plates made of aluminum alloy 6056T4 used for manufacturing fuselage panels under complex industrial boundary and load conditions to laser beam welding. Single pass fusion welding with laser beam was performed on several test boards. Use thermocouples to record temperature history. By macroscopic inspection of the geometric shape of the weld seam and observation of the displacement field through 3D image correlation technology. Then use Abaqus 6.6-1 for decoupling thermodynamic analysis and compare the simulation results with experimental results. Good consistency was found between the simulation results and experimental results.

Nikhil Kumar et al. [49] used “an empirical model developed by RSM to investigate the effects of laser power, scanning speed, and pulse width on ultimate tensile strength and welding width. The results of the analysis of variance indicate that the developed model can fully predict the response within the range of input parameters. In addition, microstructure analysis and hardness and tensile performance tests were conducted on the welds of 304 stainless steel and 316 stainless steel. The results indicate that compared to high heat input, low heat input typically results in fine grain structure and improved mechanical properties, regardless of the substrate composition. Compared with 316 stainless steel, 304 stainless steel has better microstructure and mechanical properties”.

Suman Chatterjee et al. [50] conducted “experimental research on laser butt welding using pulsed Nd: YAG laser. The influence of laser parameters such as laser current, pulse width, and welding speed on the welding quality of 0.45mm thin plates was studied. Research has shown that laser current is the most important parameter in thin plate welding, as it helps to achieve good mechanical and metallurgical quality of the welded joint. The welding strength increases to a certain level with the increase of scanning speed, and then decreases. Overlapping solder joints can seriously affect the surface integrity (surface roughness) and welding strength of the welded joint. The microhardness

of the melt zone (FZ) is higher than that of the heat affected zone (HAZ), due to differences in grain structure (coarseness) caused by cooling rate. Laser pulse energy has a significant impact on the generation of residual stresses in welded joints. The study was extended using nonlinear regression analysis to develop an empirical relationship between laser parameters and welding strength. The adequacy of the empirical model was verified by comparing the results obtained from the empirical model and experimental values”.

Yu Jie [51] studied the influence of channel structure parameters on the stiffness of metal bipolar plates through Abaqus modeling. Channel structure parameters include channel wall thickness, ridge width, and channel height. The simulation results show that the wall thickness of the flow channel has the greatest impact on the stiffness and stability of the metal bipolar plate, while the gas pressure has the smallest impact. Simultaneously reducing the wall thickness of the flow channel, increasing the ridge width, and increasing the height of the flow channel will lead to a decrease in the stability of the metal bipolar plate structure.

Xiao Chaoyang [52] studied the stacking welding of metal bipolar plates, explored the main forms of deformation after bipolar plate welding, and designed a set of fixtures and welding processes based on this to determine the degree of influence of welding joints. The results showed that the main deformation after metal bipolar plate welding was angular deformation, with a minimum deformation of 0.36 mm and a maximum deformation of 0.54 mm. The maximum deformation at the weld seam is about 1.65 mm. Using fixtures during laser welding can effectively reduce its deformation. Through finite element analysis, the maximum deformation does not exceed 0.2 mm. The degree of influence of welding process parameters on welding joints varies from high to low, including welding power, welding speed, defocus amount, and pulse width.

4. CONCLUSION

The research on welding formation of bipolar plates in proton exchange membrane fuel cells is important for environmental protection; Optimization of energy structure; The development of the economy has significant implications. In terms of environmental protection, the research on the welding of proton

exchange membrane bipolar plates has accelerated the development and production of hydrogen energy vehicles, gradually replacing traditional fuel vehicles. This can effectively reduce the emissions of greenhouse gases such as carbon dioxide and sulfur dioxide, thereby reducing the occurrence of adverse weather conditions such as acid rain, and providing great help in achieving the goal of carbon peak and carbon neutrality. In terms of optimizing the energy structure, the research on welding and forming of bipolar plates for proton exchange membrane fuel cells can effectively promote the popularization of hydrogen energy vehicles and hydrogen energy, thereby reducing the proportion of traditional fossil fuels such as oil, and achieving the goal of protecting energy security. At the same time, it can also change the long-standing shortage of fossil fuels. In terms of economic development, the research on the welding of bipolar plates in proton exchange membrane fuel cells has increased the utilization rate of hydrogen energy vehicles, injected a shot in the arm into the automotive industry, promoted the optimization and upgrading of the automotive industry and its related industrial chain, and provided tremendous assistance for economic development. This article's research on fuel cell bipolar plates can serve as a fundamental understanding and reference, providing background guidance for future research. However, current research on bipolar plates is still too idealistic and has not been combined with engineering practice. Future researchers can study the welding of fuel cell bipolar plates from the perspective of engineering practice.

DISCLAIMER (ARTIFICIAL INTELLIGENCE)

Author(s) hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc.) and text-to-image generators have been used during the writing or editing of this manuscript.

ACKNOWLEDGEMENTS

Thank you to my senior brother, fellow students, and junior brother for helping me search for literature related to my paper, which enabled me to write a literature review.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Aminzadeh A, Parvizi A, Safdarian R, Rahmatabadi D. Comparison between laser beam and gas tungsten arc tailored welded blanks via deep drawing. Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture. 2021;235(4): 673-688.
DOI: 10.1177/0954405420962391
2. Behera MP, Dougherty T, Singamneni S. Selective laser melting of stainless steel and silicon nitride fibre metal matrix composites. Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture. 2020;234(12): 1513-1525.
DOI: 10.1177/0954405420928684
3. Qiu Y, Shen W, Yan R, Xu L, Liu E. Fatigue reliability evaluation of thin plate welded joints considering initial welding deformation. Ocean Engineering. 2021;236: 109440.
DOI: 10.1016/j.oceaneng.2021.109440
4. He Y, Zeng Y, Li Z. et al. The effect of laser segmented skip welding on welding distortion and residual stress in butt weld of 6061 aluminum alloy thin plate. Int J Adv Manuf Technol. 2023;124:3293–3309.
Available:https://doi.org/10.1007/s00170-022-10663-9
5. Das S, Narayanan RG. Friction stir spot welding of aluminum and steel sheets using a consumable sheet. Int J Adv Manuf Technol. 2023;128:221–241.
Available:https://doi.org/10.1007/s00170-023-11863-7
6. Liinalampi Sami, Remes, Heikki Lehto, Pauli Lillemäe, Ingrid Romanoff, Jani Porter, David. Fatigue strength analysis of laser-hybrid welds in thin plate considering weld geometry in microscale. International Journal of Fatigue. 2016;87():143–152.
DOI: 10.1016/j.ijfatigue.2016.01.019
7. de Paula Macanhan, Vanessa Bawden, Correa, Edmilson Otoni, de Lima, Antonio Marcos Gonçalves, da Silva, Jose Tadeu. Vibration response analysis on stainless steel thin plate weldments. The International Journal of Advanced Manufacturing Technology; 2019.
DOI: 10.1007/s00170-019-03297-x
8. Pengfei Zhao, Xiaobin Zhang, Shuwang Bian, Wenlong Zhang, Zhanyi Cao. Effect of preheating temperature on the defects in pulsed laser welding of sheet AZ31 magnesium alloy, Materials Letters. 2023; 135438.
Available:https://doi.org/10.1016/j.matlet.2023.135438
9. Tobias Valentino, Andreas Stephen, Tim Radel, Frank Vollertsen. Applicability of a laser pre-treatment for a robust subsequent bending of thin sheet metal, CIRP Journal of Manufacturing Science and Technology. 2023;44:45-54.
Available:https://doi.org/10.1016/j.cirpj.2023.05.001
10. Roy JG, Yuvaraj N, Vipin. Effect of welding parameters on mechanical properties of cold metal transfer welded thin AISI 304 Stainless-Steel Sheets. Trans Indian Inst Met. 2021;74:2397–2408.
Available:https://doi.org/10.1007/s12666-021-02326-2
11. Jae, Woong, Kim, et al. A study on an efficient prediction of welding deformation for T-joint laser welding of sandwich panel[J]. International Journal of Naval Architecture and Ocean Engineering. 2014;6(2):245-256.
12. Mato Perić, Karlo Seleš, Zdenko Tonković, Martina Lovrenić-Jugović. Numerical simulation of welding distortions in large structures with a simplified engineering approach. Open Physics; 2019.
DOI: 10.1515/phys-2019-0076
13. Ma, Ninshu, Huang, Hui, Murakawa, Hidekazu. Effect of jig constraint position and pitch on welding deformation. Journal of Materials Processing Technology. 2015; 221():154–162.
DOI: 10.1016/j.jmatprotec.2015.02.022
14. Kumar, Nikhil, Mukherjee, Manidipto, Bandyopadhyay, Asish. Comparative study of pulsed Nd: YAG laser welding of AISI 304 and AISI 316 stainless steels[J]. Optics & Laser Technology. 2017;8824-39.
DOI: 10.1016/j.optlastec.2016.08.018
15. Morgan Dal, Remy Fabbro. [INVITED] An overview of the state of art in laser welding simulation. Optics and Laser Technology. 2016;78:2-14.
16. Lijun Han, Lei Jia, Wenchao Yu. Characteristics of welding laser beam and its influence on weld forming coefficient [J]. Journal of Physics: Conference Series. 2024;2671(1).
DOI: 10.1088/1742-6596/2671/1/012003.
17. Wojciech Suder, Xin Chen, David Rico Sierra, et al. Control of meltpool shape in laser welding[J]. Welding in the World. 2024;68(6):1485-1495.

- DOI: 10.1007/s40194-024-01719-3.
18. Zunyuehuang, Zhenluo, Sansanao, et al. Effect of laser welding parameters on weld bowing distortion of thin plates [J]. *High Temperature Materials and Processes*. 2018;37(4):299-311.
DOI: 10.1515/htmp-2016-0153.
 19. Li S, Xu W, Xiao G, Chen B. Weld formation in laser hot-wire welding of 7075 Aluminum Alloy. *Metals*. 2018;8:909.
Available:https://doi.org/10.3390/met8110909
 20. Nisar S, Noor A, Shah A, et al. Optimization of process parameters for laser welding of A5083 aluminium alloy [J]. *Optics & Laser Technology*. 2023; 163.
DOI: 10.1016/j.optlastec.2023.109435
 21. Danny P'ng. Q-switch Nd: YAG laser welding of AISI 304 stainless steel foils[J].*Materials Science and Engineering*. 2008;486(1-2):680–685.
 22. Brady MP, Elhamid M. Abd. Manufacturing and performance assessment of stamped, laser welded, and nitrided FeCrV stainless steel bipolar plates for proton exchange membrane fuel cells[J]. *International Journal of Hydrogen Energy*. 2013;38(11): 4734–4739.
DOI: 10.1016/j.ijhydene.2013.01.143
 23. Pakmanesh R M, Shamanian M, Ashrafi A. Effects of Nd: YAG Pulsed Laser Welding Parameters on the Electrochemical Corrosion Properties of Carbon-Coated 316L Foils in a Simulated PEMFC Environment [J]. *Transactions of the Indian Institute of Metals*. 2020;73(1):169-180.
 24. Nawi I, Saktioto, Fadhali M, et al. Nd: YAG laser welding of stainless steel 304 for Photonics Device Packaging [J]. *Procedia Engineering*. 2011;8374-379.
 25. Yi-Chun Liao, Ming-Huei Yu. Effects of laser beam energy and incident angle on the pulse laser welding of stainless steel thin sheet [J]. *Journal of Materials Processing Technology*. 2007;190(1-3): 102–108.
 26. Afonso V V, Roberto J B, Wagner R D. Pulsed Nd: YAG laser seam welding of AISI 316L stainless steel thin foils [J]. *Journal of Materials Processing Tech*. 2010;210(14):1838-1843.
 27. Zuguo L, Dabin Z, Xiangzhong J, et al. Suppression of deformation and enhancement of weld properties in thin stainless steel using synchronous heat sink + ultrasonic hybrid laser welding [J]. *Journal of Materials Processing Tech*. 2023;322.
 28. Dean D, Yijun Z, Tao B, et al. Experimental and numerical investigations of welding distortion induced by CO₂ post-welding gas arc welding in thin-plate bead-on joints [J]. *Materials and Design*. 2013;52720-729.
 29. Adak M, Mandal N. Numerical and experimental study of mitigation of welding distortion [J]. *Applied Mathematical Modelling*. 2009;34(1):146-158.
 30. Zhan X, Liu X, Wei Y, et al. Numerical simulation on backward deformation of MIG multi-layer and multi-pass welding of thick Invar alloy [J]. *The International Journal of Advanced Manufacturing Technology*. 2017;92(1-4):1001-1012.
 31. Guirao J, Rodríguez E, Bayón A, et al. FEM simulation of a small EB welded mock-up and new sequence proposed to improve the final distortions [J]. *Fusion Engineering and Design*. 2009;85(2):181-189.
 32. Youmin R, Yu H, Jiajun X, et al. Numerical simulation and experiment analysis of angular distortion and residual stress in hybrid laser-magnetic welding [J]. *Journal of Materials Processing Tech*. 2016; 245270-277.
 33. Zhang W, Fu H, Fan J, et al. Influence of multi-beam preheating temperature and stress on the buckling distortion in electron beam welding [J]. *Materials Design*. 2018;139439-446.
 34. Casalino, Giuseppe, et al. Laser offset welding of AZ31B magnesium alloy to 316 stainless steel. *Journal of Materials Processing Technology*. 2017;242:49-59.
 35. Tao T, Dianwu Z, Jinshui L, et al. Improvement of laser welded joint properties of AZ31B magnesium alloy to DP590 dual-phase steel produced by external magnetic field [J]. *Journal of Manufacturing Processes*. 2022;79270-283.
 36. Suman C, NLT, Dongkyoung L. Mechanical and microstructural investigation of dissimilar joints of Al-Cu and Cu-Al metals using nanosecond laser [J]. *Journal of Mechanical Science and Technology*. 2022;36(8):4205-4211.
 37. Fengyuan S, Sicheng N, Baohua Z, et al. Influence of scan line spacing on nanosecond pulse laser welding of 6063 Al to steel thin sheets [J]. *Optics and Laser Technology*. 2022;145.
 38. Abderrazak K, Kriaa W, Salem B W, et al. Numerical and experimental studies of

- molten pool formation during an interaction of a pulse laser (Nd: YAG) with a magnesium alloy [J]. *Optics Laser Technology*. 2009;41(4):470-480.
39. Artinov A, Bachmann M, Rethmeier M. Equivalent heat source approach in a 3D transient heat transfer simulation of full-penetration high power laser beam welding of thick metal plates [J]. *International Journal of Heat and Mass Transfer*. 2018; 1221003-1013.
 40. Wu S C, Wang G H, Zhang Y. A new heat source model for Keyhold plasma arc welding in fem analysis of the temperature profile [J]. *Welding Journal*. 2006;85(12): 284-291(s).
 41. Attar A M, Ghoreishi M, Beiranvand M Z. Prediction of weld geometry, temperature contour and strain distribution in disk laser welding of dissimilar joining between copper 304 stainless steel [J]. *Optik*. 2020;219165288-.
 42. Jazeel CR, MV, SM, et al. Simulation of laser butt welding of AISI 316L stainless steel sheet using various heat sources and experimental validation [J]. *Journal of Materials Processing Tech*. 2014;21948-59.
 43. Ahmad G N, Raza M S, Singh N K, et al. Experimental investigation on Ytterbium fiber laser butt welding of Inconel 625 and Duplex stainless steel 2205 thin sheets [J]. *Optics & Laser Technology*. 2020;126: 106117.
 44. Ismail M I S, Okamoto Y, Okada A. Thermo-mechanical analysis on thermal deformation of thin stainless steel in laser micro-welding [J]. *International Journal of Manufacturing, Materials, and Mechanical Engineering (IJMMME)*. 2016;6(2):51-66.
 45. Pankaj P, Tiwari A, Biswas P. Transient thermal analysis of CO 2 laser welding of AISI 304 Stainless Steel Thin Plates [M] // *Manufacturing Engineering*. Springer, Singapore. 2019;49-65.
 46. Kim T, Suga Y, Koike T. Welding of thin steel plates by hybrid welding process combined TIG arc with YAG laser [J]. *JSME International Journal Series A Solid Mechanics and Material Engineering*. 2003; 46(3):202-207.
 47. Farid M, Molian P A. High-brightness laser welding of thin-sheet 316 stainless steel [J]. *Journal of Materials Science*. 2000;35(15): 3817-3826.
 48. Zain-UI-Abdein M, Nelias D, Jullien J F, et al. Thermo-mechanical analysis of laser beam welding of thin plate with complex boundary conditions [J]. *International Journal of Material Forming*. 2008;1(1): 1063-1066.
 49. Kumar N, Mukherjee M, Bandyopadhyay A. Comparative study of pulsed Nd: YAG laser welding of AISI 304 and AISI 316 stainless steels [J]. *Optics & Laser Technology*. 2017;88:24-39.
 50. Chatterjee S, Mahapatra S S, Bharadwaj V, et al. Parametric appraisal of mechanical and metallurgical behavior of butt welded joints using pulsed Nd: YAG laser on thin sheets of AISI 316 [J]. *Optics & Laser Technology*. 2019;117:186-199.
 51. Yu Jie. Design and analysis of thin shell metal bipolar plate structure for fuel cells [D]. Dalian University of Technology; 2020.
 52. Xiao Chaoyang. Research on laser stacking welding process of ultra thin stainless steel Bipolar plates for fuel cells [D]. Hunan Hunan Hunan Hunan University of Technology; 2021.

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of the publisher and/or the editor(s). This publisher and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.

© Copyright (2024): Author(s). The licensee is the journal publisher. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:
The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/123803>